



CMC White A-06 101984

Application:

This product has been developed for thin mono and multilayered films, requiring high level of dispersion and opacity. It is particularly suitable for lamination grade films.

General Characteristics:

- | | | |
|---------------------------------------|---|-------------------------|
| • Appearance | : | White pellets |
| • Carrier Resin | : | Polyethylene |
| • TiO ₂ Equivalent Content | : | 70% (equivalent) |
| • Bulk Density [kg/m ³] | : | 1350 - 1450 |
| • Pellets/gramme | : | 20-30 |
| • MFI (190C/2.16kgs) | : | 12 ± 4 (gms/10 minutes) |
| • Specific Gravity | : | 2.3 |
| • Dispersion in 25micron film | : | Excellent |

Storage

To be used within 6 months. Not to be stored in direct sunlight.

Packing

25 kgs in plastic woven sacks

Issued: 14th December, 2005

Revised:

The information on our products and recommendations on their use are based on our present knowledge and experience. They are given in good faith solely for the consideration of the users. As many factors affect the use of our products and since the conditions of use are beyond our control, all recommendations or suggestions are presented without guarantee or responsibility on our part. Users are advised to carry out their own tests and experiments to establish suitability of our products. We do not accept any liability for loss or damage, however arising which may directly or indirectly result from the use of our products. All such risks are assumed by the user. Further more, it is the responsibility of the users of our products to ensure that any proprietary rights, existing laws and legislation are observed. Due to continuous product improvement we reserve the right to change the product specification without prior notice.